



Technical Data Sheet

REF: INM/REF-PR001/I002

Email: info@inmaa.sa

Website: www.inmaa.sa

IRON OXIDE - SYNTHETIC

Technical properties:

Test Performed	Component	Unit	Amount (%)
ASTM D1533 – 12	Water Content (KF)	%	0.460
ASTM D 7348 - 13	Loss on Ignition	%	3.32
Std Method	Calcium Oxide	%	0.10
ASTM D 5185 - 13	Magnesium Oxide	%	<0.01
ASTM D 5185 - 13	Aluminum Oxide	%	0.10
ASTM D 5185 - 13	Silicon Dioxide	%	0.01
ASTM D 5185 - 13	Ferric Oxide	%	>99.9

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.