



Technical Data Sheet

REF: INM/REF-PRO01/I004

Email: info@inmaa.sa

Website: www.inmaa.sa

IRON OXIDE

Physical Properties:

Moisture Content @ 105°C % 0.71

Chemical Properties (On Dry Basis):

Chemical Properties (On Dry Basis):			
1	Silicon Oxide (SiO ₂)	%	1.20
2	Iron Oxide (Fe ₂ O ₃)	%	98.0
3	Aluminum Oxide (Al ₂ O ₃)	%	0.20
4	Manganese Oxide (MnO)	%	0.14
5	Copper Oxide (CuO)	%	0.01
6	Zinc Oxide (ZnO)	%	0.01
7	Chloride (Cl)	%	LT 0.01
8	Sulphur Trioxide (SO ₃)	%	LT 0.01
9	Sodium Oxide (SO ₃)	%	0.03
10	Potassium Oxide	%	LT 0.01
11	Calcium Oxide (CaO)	%	LT 0.01
12	Magnesium Oxide (MgO)	%	LT 0.01
13	Chromium Oxide (Cr ₂ O ₃)	%	LT 0.03
14	Lead Oxide (PbO)	%	LT 0.01

LT = Less than the detection limit

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.